



Tender specifications PRIME STONE collection

Supply of Panaria Ceramica porcelain stoneware tiles for walls and floors.

Product characteristics

Panaria Ceramica full body porcelain stoneware tiles, unglazed, composed of a very fine mixture of quality clay with the addition of feldspar, quartz and kaolin, manufactured by dry pressing of atomized powders and subsequently sintered by industrial firing at temperatures above 1200°C.

The complete vitrification of the tiles allows for a compact, non-absorbent, frost-proof product, resistant to bending, impacts, staining, chemical attack and thermal shock.

Compliance with EN 14411-G / ISO 13006-G

The Prime Stone collection is in compliance with the regulations required for first quality products in Italy and Europe UNI EN 14411-G and internationally through ISO 13006-G.

Quality and environmental certifications

The conservation of the product characteristics is guaranteed by the Quality Management System put into practice by Panaria Ceramica in its plants and certified in accordance with UNI EN ISO 9001.

The collection is manufactured in plants with UNI EN ISO 14001 certified Environmental Management Systems (internationally recognized standard) and EMAS (Regulation 1221/09 - eco-management and audit community system).

The collection helps to meet the criteria for obtaining LEED credits. The content of "pre-consumer" recycled material is 40%, as certified by a qualified external body (LEED V4 Regulations - MR Credit). The product contains no VOC (volatile organic compounds). The Environmental Product Declaration (EPD) is available, this tool communicates clearly the environmental performances of the Prime Stone collection based on its Life Cycle Assessment (LCA).

Antibacterial properties

Thanks to Protect antibacterial technology, the tiles from the Prime Stone collection have continuous, effective and durable protection against the proliferation of bacteria, tested and certified in accordance with ISO 22196 and ASTM E3031.

Commercial description of the product		
Company	PANARIA CERAMICA (Panariagroup Industrie Ceramiche S.p.A.)	
Collection	PRIME STONE	
Colours	WHITE PRIME, SAND PRIME, SILVER PRIME, GRIGE PRIME, BLACK PRIME	
Sizes	30X60cm SOFT RECT	15X60cm STRUTTURATO RECT (SILVER PR., SAND PR.)
	60X60cm SOFT RECT	20X60cm STRUTTURATO RECT (SILVER PR., SAND PR.)
	45X90cm SOFT RECT	30X60cm STRUTTURATO RECT (SILVER PR., SAND PR.)
	90X90cm SOFT RECT	60,3X60,3cm STRUTTURATO (SILVER PR., SAND PR.)
	60X60cm LUX RECT	45X90cm-20mm RECT STRUTTURATO (except WHITE PR.)
	45X90cm LUX RECT	45,5X91,4cm-20mm STRUTTURATO (except WHITE PR.)
Superfici	90X90cm LUX RECT	
	SOFT LUX - The LUX finishes are recommended, as well as for wall cladding, also for flooring in residential or light commercial areas that are not subjected to heavy traffic, where anti-slip characteristics are not required. The occasional presence of small inconsistencies or little spots on the surface is to be considered a characteristic of the material and of its unique production process. If the product is laid in direct contact with external environments, it is recommended to use protective solutions to reduce the formation of scratches. STRUTTURATO (*)	
Bordi	RECTIFIED (RECT), NOT RECTIFIED	
Spessori	10mm - 11mm - 20mm	

(*) The antimicrobial protection is not applied.



EMAS



ISO 14001



40%



LEED



LEED



ISO 9001



ANTIBATTERICO



MARCHIO CE



MADE IN ITALY



EPD



Tender specifications PRIME STONE collection

Technical features

Product type: full body porcelain stoneware (UGL)

According to: ISO 13006-G (Group Bla), EN 14411-G (Group Bla)

Technical features		Test method	Required values - ISO 13006-G, EN 14411-G - Bla-UGL Group	Average values PRIME STONE
Water absorption		ISO 10545-3	≤ 0,5 %	0,05 %
Breaking strength (S)		ISO 10545-4	≥ 1300 N	Thickness 10mm: 2500 N Thickness 11mm: 3000 N Thickness 20mm: 13600 N
Modulus of rupture		ISO 10545-4	≥ 35 N/mm ²	50 N/mm ²
Deep abrasion resistance		ISO 10545-6	≤ 175mm ³	145mm ³
Linear thermal expansion		ISO 10545-8	No provision	$\alpha \leq 7 \cdot 10^{-6} \text{ } ^\circ\text{C}^{-1}$
Stain resistance		ISO 10545-14	Class 3 Min.	5 RESISTANT ≥ 3 (LUX)
Chemical resistance (*)		ISO 10545-13	As indicated by manufacturer	LA, HA RESISTANT
Frost resistance		ISO 10545-12	No alteration	RESISTANT
Dimensions	Lenght and width	ISO 10545-2	RECT ± 0,3 %, max ± 1 mm ± 0,6 %, max ± 2 mm	COMPLIANT
	Straightness of sides	ISO 10545-2	RECT ± 0,3 %, max ± 0,8 mm ± 0,5 %, max ± 1,5 mm	COMPLIANT
	Rectangularity	ISO 10545-2	RECT ± 0,3 %, max ± 1,5 mm ± 0,5 %, max ± 2 mm	COMPLIANT
	Warpage	ISO 10545-2	RECT ± 0,4 %, max ± 1,8 mm ± 0,5 %, max ± 2 mm	COMPLIANT
	Thickness	ISO 10545-2	± 5 % ± 0,5mm	COMPLIANT
Slip resistance		DIN 51130	-	R9 (SOFT) R11 (STRUTTURATO, 20mm)
		DIN 51097	-	A+B+C (STRUTTURATO, 20mm)
		BCR-TORTUS	-	$\mu > 0,40$ (SOFT, STRUTTURATO, 20mm)
		ANSI A326.3	-	DCOF ≥ 0.42 (SOFT, STRUTTURATO, 20mm)
		AS/NZS 4586	-	P4 (STRUTTURATO, 20mm)
		BS 7976-2	-	36+ (STRUTTURATO, 20mm)
Shade variation		ANSI A137.1	As indicated by manufacturer	V2
Fire reaction		EN 13823	CPR (UE) 305/2011, 2000/147/CE, UNI EN 13501-1	Class A1 (wall)
		EN 9239-1		Class A1 _{fl} (floor)
Thermal conductivity		EN 12524	-	$\lambda = 1,3 \text{ W/m } ^\circ\text{K}$
Recommended minimum joint (**)		Indoor	-	2mm (RECT) 3-4mm APPROX (NOT RECT)
		Outdoor	-	5-6mm APPROX

(*) Excluding hydrofluoric acid and its derivatives.

(**) The width of grout joints must be established by the installation supervisor, unless grout widths are regulated by national laying standards.