

# Tender specifications | SURROUND collection

Supply of Panaria Ceramica porcelain stoneware tiles for walls and floors.

#### **Product characteristics**

Panaria Ceramica coloured-body porcelain stoneware tiles, unglazed, composed of a very fine mixture of quality clay with the addition of feldspar, quartz and kaolin, manufactured by dry pressing of atomized powders and subsequently sintered by industrial firing at temperatures above 1200°C. The complete vitrification of the tiles allows for a compact, non-absorbent, frost-proof product, resistant to bending, impacts, staining, chemical attack and thermal shock.

Safetouch: cutting-edge technology that makes ceramic surfaces smoother and more pleasant to the touch, while maintaining high standards of slip resistance, hygiene, ease of cleaning and maintenance.

#### Compliance with EN 14411-G / ISO 13006-G

The SURROUND collection is in compliance with the regulations required for first quality products in Italy and Europe UNI EN 14411-G and internationally through ISO 13006-G.

### Quality and environmental certifications

The conservation of the product characteristics is guaranteed by the Quality Management System put into practice by Panaria Ceramica in its plants and certified in accordance with UNI EN ISO 9001.

The collection is manufactured in plants with UNI EN ISO 14001 certified Environmental Management Systems (internationally recognized standard) and EMAS (Regulation CE 1221/09 - eco-management and audit community system). The collection helps to meet the criteria for obtaining LEED credits. The content of "pre-consumer" recycled material is 40%, as certified by a qualified external body (LEED V4 Regulations - MR Credit).

The product contains no VOC (volatile organic compounds) and got the GREENGUARD GOLD certification.

The Environmental Product Declaration (EPD) is available, this tool communicates clearly the environmental performances of the SURROUND collection based on its Life Cycle Assessment (LCA).

For all the items in the collection, the calculation of the carbon footprint (PCF) over the entire life cycle is available, expressed as CO<sub>2</sub> equivalent per unit of product, certified according to ISO 14067.

The collection complies with the technical specifications and contractual conditions applicable to porcelain stoneware outlined in the Ministerial Decree of 23 June 2022 "Minimum environmental criteria for the contracting of the design and execution of works for building projects".

#### Antibacterial properties

Thanks to Protect antibacterial technology, the tiles from the SURROUND collection have continuous, effective and durable protection against the proliferation of bacteria, tested and certified in accordance with ISO 22196 and ASTM E3031.

Commercial description of the product						
Company	PANARIA CERAMICA (Panariagroup Industrie Ceramiche S.p.A.)					
Collection	SURROUND					
Colours	DRAFT, SKETCH, ROW, SHAPE, OUTLINE					
Sizes	15x15 cm Rect NATURALE	30x60 cm Rect NATURALE	30x60 cm Rect SOFT	30x60 cm Rect EXT		
	90x90 cm Rect NATURALE					
	60x60 cm Rect NATURALE	60x60 cm Rect SOFT	60x60 cm Rect EXT			
	60x120 cm Rect NATURALE	60x120 cm Rect SOFT	60x120 cm Rect EXT			
	60x60 cm Rect STRUTTURATO - 20 mm		60x120 cm Rect STRUTTURATO - 20 mm			
Surfaces	NATURALE (Safetouch), EXT* (Safetouch), STRUTTURATO* SOFT - Recommended for flooring in residential and low traffic commercial spaces					
Edges	RECTIFIED (RECT)					
Thickness	9 mm - 20 mm					

(\*) The antimicrobial protection is not applied.

























# Tender specifications | SURROUND collection

## **Technical features**

Product type: coloured-body porcelain stoneware (UGL)

According to: ISO 13006-G (Group Bla), EN 14411-G (Group Bla)

Technical features		Test method	Required values ISO 13006-G / EN 14411-G Bla-UGL Group	Average values SURROUND
Water absorption		ISO 10545-3	≤ 0,5%	0,05%
Breaking strength (S)		ISO 10545-4	≥ 1300 N	Thickness 9 mm: 2200 N Thickness 20 mm: 13600 N
Modulus of rupture		ISO 10545-4	≥ 35 N/mm <sup>2</sup>	50 N/mm <sup>2</sup>
Deep abrasion resistance		ISO 10545-6	≤ 175 mm³	145 mm <sup>3</sup>
Linear thermal expansion		ISO 10545-8	No provision	α ≤ 7·10 <sup>-6</sup> °C <sup>-1</sup>
Stain resistance		ISO 10545-14	Class 3 min.	5 RESISTANT
Chemical resistance (*)		ISO 10545-13	As indicated by manufacturer	LA, HA RESISTANT
Frost resistance		ISO 10545-12	No alteration	RESISTANT
Dimensions	Lenght and width	ISO 10545-2	± 0,3%, max ± 1 mm	COMPLIANT
	Straightness of sides	ISO 10545-2	± 0,3%, max ± 0,8 mm	COMPLIANT
	Rectangularity	ISO 10545-2	± 0,3%, max ± 1,5 mm	COMPLIANT
	Warpage	ISO 10545-2	± 0,4%, max ± 1,8 mm	COMPLIANT
	Thickness	ISO 10545-2	± 5% ± 0,5 mm	COMPLIANT
Slip resistance		DIN EN 16165 - Annex B	-	R10 (NATURALE) R11 (EXT, STRUTTURATO 20 mm)
		DIN EN 16165 - Annex A	-	B (NATURALE) C (EXT, STRUTTURATO 20 mm)
		BCR-TORTUS	-	μ > 0,40 (NATURALE, EXT, STRUTTURATO 20 mm)
		ANSI A326.3	-	ID - DCOF ≥ 0.42 (Dry): NATURALE, SOFT IW - DCOF ≥ 0.42 (Wet): NATURALE IW+: NATURALE (***) EW: EXT, STRUTTURATO 20 mm
		AS/NZS 4586	-	P3 (NATURALE) P4 (EXT, STRUTTURATO 20 mm)
		BS EN 16165 - Annex C	-	PTV 36+Wet (SI.96): NATURALE PTV 36+Wet (SI.96 - SI.55): EXT, STRUTTURATO 20 mm
Shade variation		ANSI A137.1	As indicated by manufacturer	V2
Fire reaction		EN 13823	CPR (UE) 305/2011, 2000/147/CE,	Class A1 (wall)
		EN 9239-1	UNI EN 13501-1	Class A1 <sub>fl</sub> (floor)
Thermal conductivity		EN 12524	-	λ = 1,3 W/m °K
Recommended minimum joint (**)		Indoor	-	2 mm (RECT)
		Outdoor	-	5-6 mm approx

<sup>(\*)</sup> Excluding hydrofluoric acid and its derivatives.





















<sup>(\*\*)</sup> The width of grout joints must be established by the installation supervisor, unless grout widths are regulated by national laying standards.

<sup>(\*\*\*)</sup> With the exception of areas characterized by a higher risk of slipping (such as public showers, indoor swimming pools, etc.) for which an anti-slip surface is recommended (EXT).